

Patent Abstracts of Japan

ing thin film of fullerene on a
-100nm thickness on a
deposition or sputtering or
dissolving fullerene in a
electron beams in
part is dissolved and